



CUSTOMER SPECIFICATION

Style No: 784405
Finish No: 849
Customer End Use: Hospital Privacy Curtain
Description: Square Root
Content: 100% Polyester Visa Intrinsic FR
AM and DWR

Date Original: 8/1/2019
Date Revised: 08/01/19

Finished Requirements

Weave		Square Root
Width	ASTM D-3774	73.5" +/- 1" OA
Weight (oz./sq yd)	ASTM D-3776	5.50 +/- .3
Oz. Per Linear Yd.	ASTM D-3776	11.35 +/- .5
Ends	ASTM D-3775	115 +/- 3
Picks	ASTM D-3775	57 +/- 3
Bias/Bow	ASTM D-3882	2" max
Tensile (grab)	ASTM D-5034	125 Warp x 75 Fill min
Seam Slippage	ASTM D-434	25 Warp x 25 Fill min
Shrinkage (wash)	AATCC-135	2.5% Warp x 2.5% Fill max
120 Degrees F		1 & 5 Wash Cycles
Antimicrobial	XRF	Pass
Flame Resistance	1989 NFPA 701	Pass 1989 NFPA 701
Shade: DataColor		Delta E +/- 1.0
Light Fastness:	AATCC 16-2004	4.0 min @ 40 hrs
Crocking:	AATCC 8-1981	Wet / Dry 4.0 min
Wash Fastness:	AATCC 61-1996	3.5 min - Polyester
Solvent Bleed:	AATCC 132-2009	4.0 min
Crocking	AATCC 8-1981	4
Repel	water drop test	60 Sec Min
Repel	AATCC 22-1996	70 Spray minimum

Put-Up Requirements

Target Roll Length	60
Max roll length	65
Min roll length	30
Seams Per Roll	1 Max.
Min. Pc. Between seams	30 Yds.
Tube Diameter	2" I.D. MIN.
Tube Wall	0.275" Min.
Core Plugs	No
Type Wrap	Polywrap
Type Seam	Merrow
Tube Length	59
Defects/100 yds.	5 Maj, 20 Pts. tot.

All Rolls To Be Rolled Face In

WASHING INSTRUCTIONS

• Ensure laundering machinery is free of burrs or sharp objects that can cause snagging ▪ Wash with like colors
▪ Do not combine with other product (i.e towels, sheets, napery, etc.) ▪ Do not overload machinery ▪
Machine wash, warm (120°-160° F) ▪ Use non-chlorine bleach if needed ▪ Do not use any fabric softeners ▪
Dry with like colors and products ▪ Do not overload the dryer ▪ Tumble dry on medium ▪ Promptly remove
from dryer ▪ Use iron on low setting if needed.